

WE CLAIM:

1. A catalyst for treating an exhaust gas stream comprising:
a NO_x occluding catalyst structure having an outer layer
comprising an alkaline earth component and a rare earth component.

2. The catalyst of Claim 1 wherein the outer layer comprises an
alkaline earth component in an amount of at least about 30 weight percent and a rare earth
component in an amount of not more than about 70 weight percent.

3. The catalyst of Claim 2 wherein the outer layer comprises an
alkaline earth component in an amount of at least about 50 weight percent and a rare earth
component in an amount of not more than about 50 weight percent.

4. The catalyst of Claim 3 wherein the outer layer comprises an
alkaline earth component in an amount of at least about 70 weight percent and a rare earth
component in an amount of not more than about 30 weight percent.

5. The catalyst of Claim 1 wherein the alkaline earth component is
selected from the group consisting of calcium, strontium, barium, and mixtures thereof.

6. The catalyst of Claim 5 wherein the alkaline earth component is
calcium.

SUBC1

SUBC2

SUBC3

SUBC4

SUBC5

- Sub E1

13. The catalyst of Claim 1 wherein the outer layer comprises a binder selected from the group consisting of acidic aluminum oxide sol, alkaline aluminum oxide sol, ammonium aluminum oxide sol, and mixtures thereof.

14. The catalyst of Claim 13 wherein the outer layer comprises an ammonium aluminum oxide sol binder.

15. The catalyst of Claim 13 wherein the outer layer comprises a binder in an amount at least about 2 wt% and less than about 6 wt%.

16. A catalyst for treating an exhaust gas stream comprising:
a NO_x occluding catalyst structure comprising an alkaline earth exchanged zeolite and an alkaline earth alumina having an outer layer comprising an alkaline earth oxide component, a rare earth oxide component, a surface area stabilizer, and a ceramic oxide binder

17. The catalyst of Claim 16 for treating an exhaust gas stream comprising:

a NO_x occluding catalyst structure having an outer layer comprising at least about 30 wt% alkaline earth oxide component, not more than about 59 wt % rare earth oxide component, not more than about 7 wt% surface area stabilizer, and not more than about 4 wt% ceramic oxide binder.

18. The catalyst of Claim 16 for treating an exhaust gas stream comprising:

a NO_x occluding catalyst structure having an outer layer comprising at least about 50 wt% alkaline earth oxide component, not more than about 42 wt % rare earth oxide component, not more than about 5 wt% surface area stabilizer, and not more than about 3 wt% ceramic oxide binder.

19. The catalyst of Claim 16 for treating an exhaust gas stream comprising:

a NO_x occluding catalyst structure having an outer layer comprising about 70 wt% alkaline earth oxide component, about 25 wt % rare earth oxide component, about 3 wt% surface area stabilizer, and about 2 wt% ceramic oxide binder.

20. A catalyst for treating an exhaust gas stream comprising:

a NO_x occluding catalyst structure having an outer layer comprising at least about 70 wt% calcium oxide component, not more than about 25 wt % neodymium oxide component, not more than about 3 wt% zirconium surface area stabilizer, and at least about 2 wt% ammonium aluminum oxide sol binder.

SUBET

Add a4

Add c4